

CLASSIC DURA HEAT AWAY Heat Insulation Coating



- High water resistance. The expanded microspheres present in the coating do not absorb water.
- Have higher water vapour permeability than corresponding standard coatings.
- Dirt pick-up resistance. The UV-crosslinking technology of the acrylic binder has been optimized to guarantee a low dirt pick-up performance.
- Extrudation: Very low extrudation when applied at low temperature and high humidity.
- Shortened drying time. Due to the high volume solids of the expanded microspheres the drying time is shortened.

USAGE

Surfaces like concrete, wood and metal sheets of exterior roofs and walls of houses, buildings, industrial facilities and warehouses could be protected by Heat reflective coatings.

DIRECTIONS FOR USE

SURFACE PREPARATION

Clean the surface thoroughly for any loose particles, fungal growth, and small vegetations. Water wash it thoroughly.

MIXING:

The thermal insulation coating could be mixed and prepared with rotational devices like dissolver, butterfly mixer or planetary mixer. Mix 1 kg of **Classic Dura Heat Away** with 400ml of water to attain brushable consistency.

APPLICATION

It is recommendable to apply a layer at dry thickness 1,0 1,5 mm to achieve a sufficient insulation. The insulation coating is easy to apply with a roller, brush or by spraying.

PROPERTIES:

Pigment volume concentration	63.7%
Volume Solids	67.7%
Weight Solids	60.0%
Density	0.80g/ Cm ³

COVERAGE:

One kg of Classic Dura Heat Away covers an area of 50 sft per coat.

PACKING: 25 kgs & 1 kg containers.



CLASSIC DURA HEAT AWAY

Heat Insulation Coating





TAMILNADU

Corporate Office

PRIMADONN BUILDTECH PVT LTD

No. 349, First Floor, Srinivasa Nagar, Kavaripettai, Gummidipoondy 601 206.

Ph+91-8220513172,

Admin Office:

No.605, Selva Vinayaga Nagar, Grant Lyon Village, Ponneri Tk., Thiruvalluvar Dt., Ph+91-6379174327, +91-8438276059.

Manufacturing Unit

No.603, Selva Vinayaga Nagar, Grant Lyon, Vadagarai, Chennai 600 052. Ph.+91-9444907177

KARNATAKA

Corporate Office:

PRIMADONN CONSTRUCTION CHEMICALS (P) LTD.,

Talacauvery Layout, Basavanagar, Bangalore 560 037. Ph.+9150878429, +91-9345411355.

PONDICHERRY

Branch Office

192/A, Chinna Subburaya Pillai Street, Near Vaikal Cutting, Puducherry 605 001. Ph.0413-4208833, 91-+9514709240

Distrubutor's

151, Chinna Subburaya Pillai Street, Near Vaikal Cutting, Puducherry 605 001. Ph.0413-2222100, 91-+9345561820

Email: Info@Primadonn.com, www.Primadonn.com

