



## CLASSIC ECO<sup>TM</sup> NAVO LIME

A Dry Mixture of Hydraulic Lime.

### Product:

Classic Eco Navo Lime is a dry mixture of hydraulic lime, calcined clay, rheology modifiers, and grain-classified quartz crushed sands is used to make Classic Eco Navo Lime Plast, a lime-clay fine plaster. Without using Portland cement, the advantages of lime and clay are combined to create the best plastering material. A porous plaster that complements older buildings or structures is navolime plast.

### How to Use:

Classic Eco Navo Lime plast in generally applied in two layers.

1. The first layer is applied in the range of 10-12mm thickness and the finishing layer is applied in the range of 3-5mm thickness.
2. Mix about 12-13 liters of water for 40 kg bag of Classic Eco Navo Lime plast and mix it thoroughly using a drill mixer preferably. It is recommended to protect the fresh plastered surfaces are fast drying for a period of 8 hours immediately after application to prevent the cracking. The surface to which the Classic Eco Navolime plast will be applied should be free from loosely attached particles and must be clean. It is advisable to dampen the surface before

plastering to avoid rapid loss of water from the plaster.

### Benefits

- Eco Friendly (Environment Sustainability)
- Breathable (It prevents damp)
- Flexible (Ease of Architectural)
- Very Attractive (Designer Plaster)
- Best Quality (Best Quality Products)

### Specification:

- Touch to Dry Time : 8-10 Hours
- Colour : Off White, Indigo, Blue, Green, Yellow, Orange
- Full Dry Time : 24 Hours
- Compressive Strength : 7-8 Mpa @ 28 Days
- Fresh Mortar Density : 1750 KG/M3

### Coverage

20 Sq.ft @ 14mm Thickness Per 40 Kg Bag



# CLASSIC ECO<sup>TM</sup> NAVO LIME

A Dry Mixture of Hydraulic Lime.



## TAMILNADU

### Corporate Office

PRIMADONN BUILDTECH PVT LTD

No. 349, First Floor, Srinivasa Nagar, Kavariipettai, Gummidipoondy 601 206.

Ph+91-8220513172,

### Admin Office:

No.605, Selva Vinayaga Nagar, Grant Lyon Village, Ponneri Tk., Thiruvalluvar Dt., Ph+91-6379174327, +91-8438276059.

### Manufacturing Unit

No.603, Selva Vinayaga Nagar, Grant Lyon, Vadagarai, Chennai 600 052. Ph.+91-9444907177

## KARNATAKA

### Corporate Office:

PRIMADONN CONSTRUCTION CHEMICALS (P) LTD.,

Talacauvery Layout, Basavanagar, Bangalore 560 037. Ph.+9150878429, +91-9345411355.

## PONDICHERRY

### Branch Office

192/A, Chinna Subburaya Pillai Street, Near Vaikal Cutting, Puducherry 605 001. Ph.0413-4208833, 91-+9514709240

### Distributor's

151, Chinna Subburaya Pillai Street, Near Vaikal Cutting, Puducherry 605 001. Ph.0413-2222100, 91-+9345561820

Email: [Info@Primadonn.com](mailto:Info@Primadonn.com), [www.Primadonn.com](http://www.Primadonn.com)

